



Recyclable



022-118-2643
Eco-friendly
Building Material



ISO9001: 2015



ISO14001: 2015

ASG[®]

Your Reliable Products

MULTI PURPOSE JOINT COMPOUND

DESCRIPTION



ASG MULTI PURPOSE READY-MIXED / NON-ASBESTOS JOINT COMPOUND Special Vinyl formulation that require minimal mixing to thinning provides a smooth seamless finish for Gypsum Board Wall, Ceiling Joints and brick wall. **ASG MULTI PURPOSE JOINT COMPOUND** used for taping, finishing Gypsum Board Joints, filling, covering and for Final Touch-Up Coats in Interior Gypsum Board applications. It is an ideal material for embedding fasteners, corner surfaces where necessary. It can also be used to repair crack on brick wall surface. It complies with ASTM C 475.

TECHNICAL REFERENCES

- **ASTM C 475** Standard Specification for Joint Compound and Joint Tape for Finishing Gypsum Board
- **ASTM C 840** Standard Specification for Application and Finishing of Gypsum Board

PRODUCT SPECIFICATION

PAIL / BUCKET	28 kg / 25kg/ 5kg
CARTON BOX	25 kg
FOR JOINT FINISHING	25 kg , Covers approx 163 fr (49.55mr)
FOR TEXTURING	25 kg , Covers approx 195 fs (18.38m2)

Store at room temperature in a cool dry location. Keep away from direct exposure to sunlight. Protect freezing. The seal to be tightly secured.

PREPARATION

- Store **ASG JOINT COMPOUND** at room temperature for 24 hours prior to the application.
- Stir content lightly, do not add water.
- Use directly from the container when use for covering embedded fasteners, corner beads and trims.
- If necessary add 1/2 pints (250ml) of water, remix gently.
- Do not add in any other material.
- Keep container covered when not in use.

SANDING

Sanding is not allowed. If required, use very fine sandpaper of grit 160.

APPLICATION



1. Apply **ASG Joint Compound** only on dry surfaces.



2. Apply thoroughly and allow each coat to dry before apply the next.



3. Keep air to the minimum, joint compound surface temperature 26/30 °C within working area until joint are completely dry.

JOINT FINISHING

- Apply the thin layer of **Joint Compound** between the Gypsum Boards Joint with 6” wide blade knife, press Joint Tape firmly into the **Joint Compound** on the Joint and embed with 8” wide blade knife.
- Sufficient joint compound must be remain under the **Joint Compound** over the embedding coat and feather out beyond the first coat.
- Allow the second coat to dry thoroughly prior to the application of the finish coat.
- Apply the final finish thin smooth coat to the joints and fasteners and let dry (Use 10” wide blade knife for joints & 6” wide blade for fasteners)

FINISH OUTSIDE CORNERS

- Fasten the Metal corner bead or metal corner tape directly to drywall.
- Apply first coat on the both sides of the external corner and let dry.
- Apply second coat slightly beyond the first coat and let dry.
- Apply the final finish thin smooth coat.

FINISH INSIDE CORNERS

- Apply the **Joint Compound** on the both sides of inside corner with 6” wide blade knife.
- Fold the Joint tape from center and press into the position.
- Embed the Joint Tape with knife.
- Excess **Joint Compound** to be removed.
- Then apply evenly a thin coat over the Joint tape on both sides and let dry.
- Apply second coat similarly slightly beyond the first coat and let dry.
- Apply the final finish thin smooth coat.

DECORATING

- Drywall surface must be clean, dry, free from dust and not glossy before any decorating.
- Decoration shall be such as painting or texturing.
- All directions by decorating shall strictly adhere according to te conditions as stipulated by decorating materials.

CAUTION

Sanding dust (from out sanding) may cause eye, nose, throat or upper respiratory irritation, long term breathing of large amounts of mica may cause lung disease. Use wet sanding technique to avoid creating dust, if dry sanded, wear a NIOSH approved dust mask. Do not take internally. The use of safety glasses is recommended.

Keep out of children's reach.

Note: **ASG** reserve the rights to revise any data without prior notice.

ASG[®]

Lot 8600, Batu11, Jalan Segenting,
Telok Panglima Garang, 42500 Selangor.

Tel: 603- 3122 8505/8515

Fax: 603- 3122 9505

HP: 6012- 3315160

Email: info@asgplaster.com
<https://www.asgplaster.com>